

46. (New) The method of claim 45, wherein the substrate comprises a floor.

47. (New) The method of claim 46, wherein the floor comprises vinyl tile.

48. (New) The method of claim 45, wherein the radiation curable coatable composition comprises an isocyanurate monomer.

49. (New) The method of claim 45, wherein the radiation curable coatable composition comprises a polymerizable monomer selected from the group consisting of an acrylated monomer, an N-vinyl monomer, a vinyl ether, and a styrenic monomer.

50. (New) The method of claim 49, wherein the polymerizable monomer is an acrylated monomer.

51. (New) The method of claim 45, wherein the radiation curable coatable composition further comprises a photoinitiator.

52. (New) A stripper for a cured coating comprising:

- (a) solvent;
- (b) a coupling agent; and
- (c) water.

53. (New) The stripper of claim 52, wherein the coupling agent is a hydrotrope.

54. (New) The stripper of claim 52, further comprising a dye.

55. (New) The stripper of claim 52, further comprising a thickening agent.

56. (New) The stripper of claim 52, further comprising a fragrance.

B1

10027933-121001

57. (New) The stripper of claim 52, further comprising a surfactant.

58. (New) The stripper of claim 52, wherein the stripper comprises water, benzyl alcohol, n-octylamine, glycolic acid, and a surfactant.

59. (New) The stripper of claim 52, wherein the stripper has a neutral pH.

60. (New) A method of stripping a cured coating on a substrate comprising:

- B1
- (a) applying the a stripper composition of claim 52 to the cured coating;
 - (b) waiting for a period of time sufficient to loosen the cured coating;
and
 - (c) removing the cured coating.

61. (New) The method of claim 60, wherein the cured coating is a cured acrylate coating.

62. (New) A primer composition comprising an acrylated latex, water, a leveling aid, and a surfactant.

63. (New) The primer of claim 62, wherein the primer has a solids content between about 2 and about 40% by weight.

64. (New) The primer of claim 63, wherein the primer has a solids content between about 2 and about 20% by weight.

65. (New) The primer of claim 64, wherein the primer has a solids content between about 4 and about 15% by weight.